



For the Ultimate in “Wet Look” Gloss with Daily Burnishing



Product Order # 17



Product Specifications

% Solids	20
pH	8.5
Specific Gravity	1.024
Viscosity, cps	15
Color	White
Coverage per gallon, sq. ft.	1,500 – 2,500
Floor Types	All finishable floor types, including VCT, terrazzo, vinyl

The UHS floor finish product designed to deliver the **ultimate** in “wet look” gloss with daily ultra high speed (UHS) burnishing.

- **Unsurpassed shine** from burnishing with propane or electric high speed 2500+ rpm burnishing
- Formulated with special acrylic copolymer technology to withstand heavy traffic & maintain high shine
- Outstanding application among a broad range of environmental conditions and application techniques
- Exceeds UL Classification as to slip resistance
- Compliant with California Air Resources Board VOC (Volatile Organic Compound) limit.

Recommended For

- Retail, Supermarkets
- Healthcare
- Government
- Commercial facilities
- Building service contractors

Hazard Rating

HMIS		NFPA
1	Health	1
0	Flammability	0
0	Reactivity	0

Another similar P&G Pro Line finish to consider: **Ambassador** is a comparable UHS finish, slightly more durable finish, designed for burnishing 3 to 5 times per week.

SIZE	DESCRIPTION
1 – 5 gal./18.9L	Ready-to-use



For the Ultimate in “Wet Look” Gloss with Daily Burnishing

DIRECTIONS FOR USE

Initial Application:



1. Remove all old wax and floor finish with appropriate PGPL Floor Finish Stripper.



2. Rinse floor thoroughly with clear water and allow to dry.
3. Using a clean, dry rayon or microfiber flat mop, apply a uniform coat of finish. Allow to dry thoroughly (typically 30-40 minutes). Apply additional coats in the same manner and let dry. For very porous or highly worn floors, one initial coat of floor sealer is recommended.

Day-to-Day Maintenance:



1. Sweep or dust mop as necessary.



2. Auto-scrubbing is recommended or damp mopping with PGPL Finish Floor Cleaner.



3. Burnish floor daily or as needed to maintain gloss.



4. Periodic deep scrub and recoat will be required to replenish the base film for best burnish results.

	YES	NO
Acrylic Copolymer Base	X	
Metal Interlock	X	
UHS Repairable	X	
UL Classified as to Slip Resistance	X	
Strips Easily	X	
DOT Regulated		X